




**LEMBAGA GETAH MALAYSIA**  
**MALAYSIAN RUBBER BOARD**  
**RUBBER RESEARCH INSTITUTE OF MALAYSIA**

**Unit Pencirian Bahan**  
260 Jalan Ampang, 50450 Kuala Lumpur.  
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.  
Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213  
Email: kartinia@lgm.gov.my



MS ISO/IEC 17025  
TESTING  
SAMM NO.069



**April 16, 2009**

**Our report no : LGM/BTK/UPB/5.10/CP/0904/0645-0650**

**SANCTUARY HEALTH SDN. BHD.**  
**No. 464, Jalan Kuala Kangsar,**  
**30100 Ipoh,**  
**Perak Darul Ridzuan.**

**Fax: 605-2921739**  
**E-mail: info@sanctuaryhealth.com.my**

**(Attention: Chang Chaur Long)**


**EXTRACTABLE PROTEIN CONTENT**

We have received samples delivered to us under your covering letter dated 03/04/2009. Analysis had been carried out as per your request. We report the following results:

Date of receipt of sample	13/04/2009
Date tested	15/04/2009
Test Method	ASTM D5712 – 2005
Sample Condition	Unaged
Type of sample	Sanctband

Sample Reference	Protein Content ( $\mu\text{g}/\text{dm}^2$ )
2. Lot No. : 051208 Colour : Orange	<50

*The sensitivity limit of the method is 50  $\mu\text{g}/\text{g}$*

  
Kartini Alias  
Research Officer  
Material Characterization Unit  
Malaysian Rubber Board  
For Director General