LEMBAGA GETAH MALAYSIA
Malaysian Rubber Board
RUBBER RESEARCH INSTITUTE OF MALAYSIA
PHYSICAL TESTING LABORATORY
Rubber Technology Centre, RRIM Research Station, 47000 Sungai Buloh, Selangor Darul Ehsan.
Main Line Tel: (6)03-61561121 Fax: (6)03-61564418
Tel: (6)03-61576748 Fax: (6)03-61563304
E-mail: ptl@lgm.gov.my

STANDARDS MALAYSIA ACCREDITED LABORATORY
MS ISO / IEC 17025
TESTING / CALIBRATION
SAMM NO.008

TEST REPORT

REPORT NO : QA/2009/0341/3 DATE : 17/04/2009

Sample Description : Testing On Tensile Strength Of Brand – Sanctband (Bands)

Marked :	Type of Sample	Colour(s)	Size
3)	Sanctband	Green (Lot No.: 051208)	0.25mm x 15cm x 1.5m

Test to Standard : ASTM D412

Date of Testing : 15/04/2009 To 16/04/2009

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (Kgf)	Elongation at Break, (%)	Modulus at 100% (Kgf)	Modulus at 200% (Kgf)	Modulus at 300% (Kgf)
QA/2009/0341/3.01	Green	368.1	820	10.1	13.9	18.3

Tensile Properties Unaged

Sample Reference	Customer Reference	Tensile Strength (MPa)	Elongation at Break, (%)	Modulus at 100% (MPa)	Modulus at 200% (MPa)	Modulus at 300% (MPa)
QA/2009/0341/3.01	Green	36.1	820	1.0	1.4	1.8

Norlee Ramli
Research Officer
Physical Testing Laboratory
for Director General MRB