



LEMBAGA GETAH MALAYSIA
MALAYSIAN RUBBER BOARD
RUBBER RESEARCH INSTITUTE OF MALAYSIA



MS ISO/IEC 17025

TESTING
SMM NO.069

Unit Pencirian Bahan

260 Jalan Ampang, 50450 Kuala Lumpur.
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.
Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213
Email: kartinia@lgm.gov.my

Our report no. : **LGM/BTK/UPB/5.10/CP/0904/0651-0656**
Your reference no. :-

May 13, 2009

Sanctuary Health Sdn. Bhd.
464, Jalan Kuala Kangsar
30010 Ipoh
Perak DR, Malaysia

Fax : 605-2921739

Attn: Chang Chaur Long

ANALYTICAL TEST RESULTS

We report the following results:

Your letter dated 03/04/2009
Date of sample received 13/04/2009
Date of testing 08/05/2009
Test method In House Method Following ASTM D6124-01
Brand Sanctband
Lot no 051208
Measurement 0.20mm x 15cm x 1.5m
Quantity Tested 4 pcs

No.	Lab. Reference No.	Sample Reference	Residual Powder Content (mg/sample*)
2.	0652	Colour Orange	0.42

* Values obtained are for whole piece of sample

“BERKHIDMAT UNTUK NEGARA”

Kartini Alias
Research Officer
Material Characterization Unit
Malaysian Rubber Board
For Director General

Page 2 of 6

The uncertainties are for a confidence probability of no less than 95%

This report is issued in accordance with the conditions of accreditation granted by SMM which has assessed the capability of the laboratory and its traceability to recognised national standards and to the units of measurement realised at the corresponding national standards laboratory. Copyright of this report is owned by the issuing laboratory and may not be reproduced other than in full except with prior written approval of the Head of the issuing laboratory.