



**LEMBAGA GETAH MALAYSIA**  
**MALAYSIAN RUBBER BOARD**  
**RUBBER RESEARCH INSTITUTE OF MALAYSIA**

**Unit Pencirian Bahan**  
260 Jalan Ampang, 50450 Kuala Lumpur.  
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.  
Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213  
Email: kartinia@lgm.gov.my



MS ISQ/IEC 17025  
TESTING  
SMM NO.069

Our report no. : **LGM/BTK/UPB/5.10/CP/0904/0651-0656**  
Your reference no. :-

**May 13, 2009**

**Sanctuary Health Sdn. Bhd.**  
**464, Jalan Kuala Kangsar**  
**30010 Ipoh**  
**Perak DR, Malaysia**

**Fax : 605-2921739**

**Attn: Chang Chaur Long**

**ANALYTICAL TEST RESULTS**

We report the following results:

Your letter dated 03/04/2009  
Date of sample received 13/04/2009  
Date of testing 08/05/2009  
Test method In House Method Following ASTM D6124-01  
Brand Sanctband  
Lot no 111208  
Measurement 0.40mm x 15cm x 1.5m  
Quantity Tested 4 pcs

No.	Lab. Reference No.	Sample Reference	Residual Powder Content (mg/sample*)
5.	0655	Colour Purple	0.62

\* Values obtained are for whole piece of sample

**“BERKHIDMAT UNTUK NEGARA”**

**Kartini Alias**  
**Research Officer**  
**Material Characterization Unit**  
**Malaysian Rubber Board**  
**For Director General**