



LEMBAGA GETAH MALAYSIA
MALAYSIAN RUBBER BOARD
RUBBER RESEARCH INSTITUTE OF MALAYSIA

Unit Pencirian Bahan
 260 Jalan Ampang, 50450 Kuala Lumpur.
 Peti Surat 10150, 50908 Kuala Lumpur, Malaysia
 Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213
 Email: kartinia@lgm.gov.my



MS ISO/IEC 17025
 TESTING
 SAMM NO.069



February 6, 2009

Our report no : LGM/BTK/UPB/5.10/CP/0902/0084

SANCTUARY HEALTH SDN. BHD.
No. 464, Jalan Kuala Kangsar,
30100 Ipoh,
Perak Darul Ridzuan.



Fax: 605-2921739

E-mail: info@sanctuaryhealth.com.my

(Attention: Chang Chaur Long)


EXTRACTABLE PROTEIN CONTENT

We have received samples delivered to us under your covering letter dated 23/01/2009. Analysis had been carried out as per your request. We report the following results:

Date of receipt of sample	03/02/2009
Date tested	06/02/2009
Test Method	ASTM D5712 – 2005
Sample Condition	Unaged
Type of sample	Sanctuary Dam

Sample Reference	Protein Content ($\mu\text{g}/\text{dm}^2$)
1. Lot No. : 181205 Colour : Green	< 50

The sensitivity limit of the method is 50 $\mu\text{g}/\text{g}$


 Kartini Alias
 Research Officer
 Material Characterization Unit
 Malaysian Rubber Board
 For Director General