

LEMBAGA GETAH MALAYSIA MALAYSIAN RUBBER BOARD


RUBBER RESEARCH INSTITUTE OF MALAYSIA



260 Jalan Ampang, 50450 Kuala Lumpur. Peti Surat 10150, 50908 Kuala Lumpur, Malaysia. Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213 Email: kartinia@lgm.gov.my



MS ISQ/IEC 17025 TESTING SAMM NO.069



April 16, 2009

Our report no

: LGM/BTK/UPB/5.10/CP/0904/0658-0663

SANCTUARY HEALTH SDN. BHD. No. 464, Jalan Kuala Kangsar, 30100 Ipoh, Perak Darul Ridzuan.

Fax: 605-2921739 E-mail: info@sanctuaryhealth.com.my

(Attention: Chang Chaur Long)

EXTRACTABLE PROTEIN CONTENT

We have received samples delivered to us under your covering letter dated 03/04/2009. Analysis had been carried out as per your request. We report the following results:

Date of receipt of sample

13/04/2009

Date tested

15/04/2009

Test Method

ASTM D5712 - 2005

Sample Condition

Unaged

Type of sample

Sanctband (Tubing)

	Sample Reference	Protein Content (μg/g)
4.	Lot No. : 150508	<50
	Colour : Blue	

The sensitivity limit of the method is 50 µg/g

Kartini Alias

Research Officer

Material Characterization Unit

Malaysian Rubber Board

For Director General

Page 4 of 6

The uncertainties are for a confidence probability of no less than 95%

This report is issued in accordance with the conditions of accreditation granted by SAMM which has assessed the capability of the laboratory and its traceability to recognised national standards and to the units of measurement realised at the corresponding national standards laboratory. Copyright of this report is owned by the issuing laboratory and may not be reproduced other than in full except with prior written approval of the Head of the issuing laboratory.