



# LEMBAGA GETAH MALAYSIA MALAYSIAN RUBBER BOARD

## RUBBER RESEARCH INSTITUTE OF MALAYSIA


### Unit Pencirian Bahan

260 Jalan Ampang, 50450 Kuala Lumpur.  
Peti Surat 10150, 50908 Kuala Lumpur, Malaysia.  
Tel: (6)03-92062000, 92063681 Fax: (6)03-42519213  
Email: kartinia@lgm.gov.my



MS ISO/IEC 17025

TESTING  
SAMM NO.069



April 16, 2009

Our report no : LGM/BTK/UPB/5.10/CP/0904/0658-0663

**SANCTUARY HEALTH SDN. BHD.**

No. 464, Jalan Kuala Kangsar,  
30100 Ipoh,  
Perak Darul Ridzuan.

Fax: 605-2921739

E-mail: info@sanctuaryhealth.com.my

(Attention: Chang Chaur Long)

### EXTRACTABLE PROTEIN CONTENT

We have received samples delivered to us under your covering letter dated 03/04/2009. Analysis had been carried out as per your request. We report the following results:

Date of receipt of sample	13/04/2009
Date tested	15/04/2009
Test Method	ASTM D5712 – 2005
Sample Condition	Unaged
Type of sample	Sanctband (Tubing)

Sample Reference	Protein Content ( $\mu\text{g/g}$ )
5. Lot No. : 150408 Colour : Purple	<50

*The sensitivity limit of the method is 50  $\mu\text{g/g}$*

Kartini Alias  
Research Officer  
Material Characterization Unit  
Malaysian Rubber Board  
For Director General